

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 March 2006 (09.03.2006)

PCT

(10) International Publication Number
WO 2006/024329 AI

(51) International Patent Classification⁷: C08J 9/00,
9/08, C08L 53/02, C08F 8/04

(21) International Application Number:
PCT/EP2004/052025

(22) International Filing Date:
3 September 2004 (03.09.2004)

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant (for all designated States except US): KRATON Polymers Research B.V. [NL/NL]; Badhuisweg 3, NL- 1031 CM AMSTERDAM (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): MUYLDERMANS, Xavier [BE/BE]; KRATON Polymers Research S.A., Monnet Centre, Avenue Jean Monnet 1, B-1348 Ottignies - Louvain-La-Neuve (BE). COIGNOUL, Emmanuelle [BE/BE]; KRATON Polymers Research S.A., Monnet Centre, Avenue Jean Monnet 1, B-1348 Ottignies-Louvain-La-Neuve (BE).

(74) Agent: KORTEKAAS, Marcel; Kraton Polymers Research B.V., Intellectual Property Services, P.O. Box 37666, NL-1030 BH Amsterdam (NL).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FOAMABLE POLYMERIC COMPOSITIONS AND ARTICLES CONTAINING FOAMED COMPOSITIONS

(57) Abstract: Foamable compositions which are usable for the manufacture of foamed, flexible, heat resistant, thermoplastic elastomeric articles, and which comprise at least: (a) 100 parts by weight of one or more selectively hydrogenated block copolymers, having at least two resinous blocks A of non-hydrogenated predominantly polymerized monovinyl arene, and a selectively hydrogenated elastomeric block B, wherein said block B prior to hydrogenation being predominantly a polymerized conjugated diene or dienes, said block copolymer having a total apparent molecular weight of at least 250 kg/mole, and containing polymerized monovinyl arene blocks of true molecular weight of at least 18 kg/mole, (b) 5 to 50, preferably from 15 to 40 parts by weight of one or more selectively hydrogenated block copolymers having at least two resinous blocks A' of non hydrogenated predominantly polymerized monovinyl arene, and an selectively hydrogenated elastomeric block B', wherein said block B' prior to hydrogenation has been derived from a polymerized conjugated diene or dienes as a major component which may be mixed with minor proportions of other copolymers (e.g. vinyl aromatic) i.e. <25 wt%, and said block copolymer having a total apparent molecular weight in the range of from 50,000 to 180,000, while the resinous blocks A' shown an true molecular weight in the range of from 3 to 20 kg/mole and preferably from 5 to 15 kg/mole, (c) from 25 to 80 parts by weight of a linear crystalline polymer comprising propylene as major component, with a Vicat softening temperature in the range of from 130°C to 180°C and a MFR in the range of from 0.5 to 30 dg/min and a polydispersity index of at least 4.5, (d) from 100 to 250 parts by weight of a softener compatible with blocks B and B', (e) from 0.01 to 3 wt%, relative to the weight of the primary components (a) up to (e) of a solid chemical nucleating agent of the endothermic group in combination with a blowing agent, and optionally (f) one or more secondary components selected from PPO and/or any resins compatible with block copolymer component (a), antioxidants, UV-stabilizers, flame retardants, surface modifying agents and inorganic fillers and foamed articles derived from said compositions.

WO 2006/024329 AI